Model: SAVANNAH TOPO 59,6X150(A)
Codes: 100330320
Water absorption: BIII - Cladding Tile (10.0% < wa <= 20.0%)
Finish: Glazed / Standard
Tone variations: V3
Rectified: Yes



Sistema DAPc® Declaración Ambiental de Productos de Construcción

## DIMENSIONAL FEATURES
UNE-EN ISO 10545-2

| | | |
|---|---|---|
| Thickness | 10.5 mm | +/-5%* |
| Width | 596 mm | |
| Length | 1500 mm | |
| Length and width deviation | Below 0.15% | +/-0.3%* |
| Side straightness deviation | Below 0.15% | +/-0.3%* |
| Squareness deviation | Below 0.15% | +/-0.3%* |
| Surface flatness deviation | Below 0.15% | +/-0.4%* |

*ISO-13006:2018 UNE-EN 14411:2016

## FEATURES

Natural-looking, non-glossy surface finish.

Name given to the finish of those tiles dimensionally improved after the firing process.

Wall installation

## MECHANICAL FEATURES
UNE-EN ISO 10545-4-6-7-9-11

| | | |
|---|---|---|
| Breaking strength | >600 N | >600 N* |
| Modulus of rupture | >15 N/mm2 | >=12 N/mm2* |
| Crazing resistance | PASS | |

*ISO-13006:2018 UNE-EN 14411:2016

## HYGIENIC FEATURES
UNE-EN ISO 10545-13-14

| | | |
|---|---|---|
| Chemical resistance | Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases | B Min.* |
| Stain resistance | Class 5. Easy cleaning with water | 3 Min.* |

*ISO-13006:2018 UNE-EN 14411:2016

## DETERMINATION OF LIGHT REFLECTANCE VALUE (LRV)
UNE-EN ISO 10545-18

| | | |
|---|---|---|
| Determination of light reflectance value (lrv) | 38.84 | |

*ISO-13006:2018 UNE-EN 14411:2016

System Certification

Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique.
Mosaic tiles must be grouted.
This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

PORCELANOSA
PORCELANOSA Grupo

## PACKING

| | | |
|---|---|---|
| Sales units per box | 2.681924 M2/BOX | |
| Sales units per pallet | 53.638477 M2/PAL | |
| Sales units per unit | 0.893975 M2/PIECE | |

## SCOPE OF USE

| | | |
|---|---|---|
| Technical code-1 | 1 - Use on walls | |

System Certification

Do not use cleaning agents containing hydrofluoric acid.
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.
For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique.
Mosaic tiles must be grouted.
This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.